

CUBA_20 S1P SRC



REZULTAT

CERTE NORMA

FETE: piele intoarsa perforata	5.4.3 Rezistenta la sfasiere 5.4.6 Coeficient de permeabilitate la vapori	178 N 4,8mg/cm ² h 48,0 mg/cm ²	≥120 N ≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²
Captuseala caputa: Material cu aerisire si rezistentala abraziune	5.5.1 Rezistenta la sfasiere 5.5.2 Rezistenta la abraziune(mediu umed) Rezistenta la abraziune(mediu uscat) 5.5.3 Coeficient de permeabilitate la vapori	25 N Fara decupaj Fara decupaj 7,7mg/cm ² h 62,0 mg/cm ²	≥ 15 N 25.600 cycles 12.800 cycles ≥ 2,0 mg/cm ² ≥20,0 mg/cm ²
Captuseala stait: Material cu aerisire si rezistentala abraziune	5.5.4 Rezistenta la sfasiere 5.5.5 Rezistenta la abraziune(mediu umed) 5.5.6 Rezistenta la abraziune(mediu uscat)	25 N Fara decupaj Fara decupaj 7,7 mg/cm ² h	≥ 15 N 51.200 cycles 25.600 cycles ≥ 2,0 mg/cm ²
Bombeu: Nemetalic dinpolicarbonat.	5.3.2 Coeficient de permeabilitate la vapori 5.3.2.3 Rezistenta la impact 5.3.2.4 Rezistenta la compresiune	62,0 mg/cm ² 14,0 mm 14,0 mm	≥20,0 mg/cm ² ≥ 14 mm ≥ 14 mm
Lamela antiperforate: Material textile rezistent la perforare	5.7.1. Grosime 5.7.3 . Absorbția de apa	3,5 mm 72 mg/cm ²	≥ 2,0 mm ≥70,0 mg/cm ²
Acoperis brant: Talpa interioara detasabila,captusita, detasabila	5.7.4.2 Rezistenta la abraziune(mediu umed) Rezistenta la abraziune(mediu uscat)	Fara decupaj Fara decupaj	25.600 cycles 12.800 cycle
Talpa: PU 2D, antistatica	5.8.2 Rezistenta la sfasiere 5.8.3 Rezistenta la abraziune 5.8.4 Rezistenta la sfasiere 5.8.5 Hidroliza 6.4.2 Rezistenta la uleiuri 5.11 Rezistenta la alunecare pe placi ceramice spalate cu detergent Alunecare pe suprafata totala a talpii Alunecare pe calcai Rezistenta la alunecare pe placi din otel acoperite cu glicerina Alunecare pe suprafata totala a talpii Alunecare pe calcai	8,3 kN/m 85 mm ³ 2,00 mm 3,00 mm 1% 0,33 0,29 0,21 0,16	≥ 8 kN/m ≤ 150 mm ³ ≤ 4,0 mm ≤ 6,0 mm ≤ 12% ≥ 0,32 ≥ 0,28 ≥ 0,18 ≥ 0,13

SIZES: 35-48; MONDOPOINT: 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg. Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it - pec: amministrazione@pec.exena.it

CUBA 20 S1P SRC



		RESULT	REQUIREMENT		
UPPER: Suede pierced leather	5.4.3 Tear strength	178 N	≥ 120 N		
	5.4.6 Water vapour permeability Coefficient	4,8mg/cm ² h 48,0 mg/cm ²	≥ 0,8 mg/cm ² h ≥ 15,0 mg/cm ²		
VAMP LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	25 N	≥ 15 N		
	5.5.2 Abrasion resistance(Wet)	No holes	25.600 cycles		
	5.5.2 Abrasion resistance(Dry)	No holes	12.800 cycles		
	5.5.3 Water vapor permeability Coefficient	7,7mg/cm ² h 62,0 mg/cm ²	≥ 2,0 mg/cm ² ≥ 20,0 mg/cm ²		
	QUARTER LINING: Breathable, abrasion resistance.	5.5.1 Tear strength	25 N	≥ 15 N	
5.5.2 Abrasion resistance(Wet)		No holes	51.200 cycles		
5.5.2 Abrasion resistance(Dry)		No holes	25.600 cycles		
	5.5.3 Water vapor permeability Coefficient	7,7 mg/cm ² h 62,0 mg/cm ²	≥ 2,0 mg/cm ² ≥ 20,0 mg/cm ²		
	SAFETY TOE CAP: Non-metallic polycarbonate safety toe.	5.3.2.3 Impact resistance	14,0 mm	≥ 14 mm	
5.3.2.4 Compression resistance		14,0 mm	≥ 14 mm		
PIERCE-RESISTANCE: Textile pierce proof footbed,	5.7.1. Thickness	3,5 mm	≥ 2,0 mm		
	5.7.3 Water absorption	72 mg/cm ²	≥ 70,0 mg/cm ²		
FOOTBED: Removable, cushioned, antistatic insole.	5.7.4.2 Abrasion resistance(Wet)	No holes	25.600 cycles		
	5.7.4.2 Abrasion resistance(Dry)	No holes	12.800 cycles		
OUTSOLE: PU 2D, Antislip sole, SRC	5.8.2 Tear strength	8,3 kN/m	≥ 8 kN/m		
	5.8.3 Abrasion resistance	85 mm ³	≤ 150 mm ³		
	5.8.4 Flexing resistance	2,00 mm	≤ 4,0 mm		
	5.8.5 Hydrolysis	3,00 mm	≤ 6,0 mm		
	6.4.2 Oils resistance	1%	≤ 12%		
	5.11 Pressed ceramic tile floor on detergent resistance	Flat slip	0,33	≥ 0,32	
		Heel slip	0,29	≥ 0,28	
		Stainless steel plate on glycerin resistance	Flat slip	0,21	≥ 0,18
			Heel slip	0,16	≥ 0,13

SIZES: 35-48; MONDOPOINT: 11

EXENA S.r.l.

Via Breda, 7/A – Zona Ind.le A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

C.F. e P. IVA: 01336080435 – Reg.Imprese MC n.01336080435 – REA MC144207

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it

DECLARATION OF CONFORMITY UE

M22 - Ver.00

As per Regulation (UE) 2016/425 - Annex IX, Exena Srl declares that the ppe and the relative production batch below described:

item **CUBA_20**

batch: **63943**



conforms to the standard: **EN ISO 20345:2011**

class: **II**

marking category: **S1 P SRC**

certificate numb.: **F-130-03271-20**

date: **30/03/2020**

issued by: **CIMAC - 0465**

Civitanova Marche
26/05/20

~~EXENA S.r.l.
Via Breda, 7/A - Zona Ind.le A
Tel. 0733 897256 Fax 0733 897519
62012 CIVITANOVA MARCHE - MC
P. IVA 01336080435~~
CEO

EXENA S.r.l.

Via Breda, 7 – Z.na Ind. A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it

DECLARAȚIE DE CONFORMITATE UE

Conform Regulamentului (UE), 20116/425 - Anexa IX, Exena Sri declară că echipamentul și lotul de producție aferent sunt descrise mai jos:

articol **CUBA_20**

serie: 63943



conform standardului: **EN ISO 20345:2011**

clasă: **II**

categoria de marcare: **S1P SRC**

certificat nr.: **F-130 -03271-20**

data: **30/03/2020**

emise de către: **CIMAC-0465**

Civitanova Marche

30.03.2020

EXENA S.r.l.
Via Breda, 7/A - Zona Ind. le A
Tel. 0733 897256 Fax 0733 897519
62012 CIVITANOVA MARCHE (MC)
P. IVA 01336080435

EXENA S.r.l.

Via Breda, 7 – Z.na Ind. A 62012 – CIVITANOVA MARCHE (MC) ITALY - Telefono: +39 0733 897256 - Fax: +39 0733 897519

P. IVA: 01336080435 - Reg. Impr. Trib. MC N. 21676/1998 - CCIAA MC 22988

www.exena.it – info@exena.it – pec: amministrazione@pec.exena.it